

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



INTERNATIONAL PATENT COOPERATION TREATY (PCT)

(43) International Publication Date
22 November 2001 (22.11.2001)

PCT

(10) International Publication Number
WO 01/87796 A1

- (51) International Patent Classification⁷: C04B 28/02, 38/10, E21B 43/02
- (21) International Application Number: PCT/EP01/05507
- (22) International Filing Date: 11 May 2001 (11.05.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
0006171 15 May 2000 (15.05.2000) FR
- (71) Applicant (for FR only): SERVICES PETROLIERS SCHLUMBERGER (SPS) [FR/FR]; 42, rue Saint Dominique, F-75007 Paris (FR).
- (71) Applicant (for AT, DE, DK, IT only): SCHLUMBERGER TECHNOLOGY B.V. [NL/NL]; Parkstraat 83-89, NL-2514 JG The Hague (NL).
- (71) Applicant (for GB only): SCHLUMBERGER HOLDINGS LIMITED [—/—]; P.O. Box 71, Craigmuir Chambers, Road Town, Tortola (VG).
- (71) Applicant (for all designated States except AT, DE, DK, FR, GB, IT): SOFITECH N.V. [BE/BE]; Rue de Stalle 140, B-1180 Brussels (BE).
- (72) Inventors; and
(75) Inventors/Applicants (for US only): DROCHON, Bruno [FR/FR]; 8, place Georges Pompidou, F-93160 Noisy-le-Grand (FR). MAROY, Pierre [BE/FR]; 2, allée Charles Nicolle, F-78530 Buc (FR).
- (74) Agent: HYDEN, Martin; Houdes et Productions Schlumberger, 1, rue Henri Becquerel, Boîte postale 202, F-92142 Clamart Cedex (FR).
- (81) Designated States (national): AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BF, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: PERMEABLE CEMENTS

(57) Abstract: The present invention concerns a cement slurry with high permeability and good compressive strength, comprising a solid fraction constituted by: 35 % to 80 % (by volume) of particles with a mean size in the range 100 microns (μ) to 800 μ ; 0 % to 15 % (by volume) of particles with a mean particle diameter in the range 0.1 microns to 10 microns; and 10 % to 40 % (by volume) of particles with a mean particle diameter in the range of 20 μ to 50 μ ; a fraction of said solid particles being constituted by a cement, and preferably a further fraction by self-destructive particles; a liquid fraction in a water/solid ratio in the range 38 % to 50 % by volume; and a percentage of cells, provided by a gas or a liquid which is not miscible with water, in the range 30 % to 60 % of the final volume of the slurry.

RECEIVED TIME MAY. 21. 8:54AM

WO 01/87796 A1

WO 01/87796

PCT/EP01/05507

PERMEABLE CEMENTS

The present invention relates to techniques for drilling oil, gas, water, geothermal, or like wells. More precisely, the invention relates to permeable cements, to a method of producing
5 such cements, and to the application of said cements to oil wells or the like.

After drilling an oil well or the like, the annular space surrounding the casing is generally cemented. Such an operation is intended to consolidate the well, to protect the casing by passivation and also, essentially, to isolate geological layers so as to prevent fluid exchange
10 between the various formation layers, where such exchange is made possible by the path formed by the drilled hole. The cementing operation is also intended to prevent gas from rising via the annular space and to limit the ingress of water into the production well.

Good isolation is thus the primary objective of the majority of cementing operations carried
15 out in oil wells or the like. However, situations arise wherein it is desired only to reinforce the casing or the geological formations that are traversed. This is particularly the case with cementing operations carried out in a reservoir and which need to be followed by perforation in order to re-establish fluid circulation between the reservoir and the well.

20 United States patent US-A-3 429 373 describes a permeable cement used to retain the sand produced by a reservoir, in particular in poorly consolidated subterranean formations. That document – and the various improvements described, for example, in US-A-3 646 998, US-A-3 654 990, US-A-3 654 991, US-A-3 654 992, US-A-3 768 561, US-A-3 861 467, US-A-3 861 467, US-A-3 862 663, and US-A-3 948 672 – describe a mixture of sand, cement
25 and water which is suspended in a hydrocarbon for injection into the formation to be treated and which is retained in the zone to be treated while the cement sets. In such formulations, the amount of cement is small compared with the other solids, and in particular the external matrix is formed by hydrocarbons, meaning that the mechanical strength of the whole formulation is very low. The purpose is clearly not that of reinforcing the casing or the walls
30 of a reservoir.

Hydrocarbons are also pollutants and are banned by law in many regions. A suspension in a hydrocarbon is not a cement slurry and in any case is not intended to reinforce the casing or

WO 01/87796

PCT/EP01/05507

the walls of a reservoir. This is supported by the very small amount of cement which is added, 7% to 25% by weight relative to the solids, which does not provide the set cement with high mechanical strength.

- 5 US-A-5 339 902 describes a means for producing permeable cement by simply foaming a conventional cement slurry with 54% to 74% by volume of water in the slurry. Permeability is obtained by means of an extreme foam quality. The quality of a foam or emulsion is defined as the ratio of the volume of the dispersed phase under certain pressure and temperature conditions to the total volume of foam or emulsion under the same conditions.
- 10 That method, which is rarely employed, leads to low compressive strengths (0.3 megapascals (MPa) in 24 hours and 1.1 MPa in 4 days), which are wholly inadequate when reinforcing casings or geological formations traversed by the well.

- Finally, Russian patent RU 2019689 describes fitting a well by replacing a portion of a casing
- 15 with a filter having pores which are obstructed by plugs that are soluble in an acid, and cementing the annular space between the filter and the wall of the well with a cement including polyvinyl chloride particles which are destroyed by heat after the cement has set.

- The aim of the present invention is to provide a method of producing a permeable cement
- 20 with sufficient compressive strength to be able to contribute to reinforcement. These very particular properties can be achieved simultaneously due to the open pore structure of the cement and to the structure of the solid portion of the permeable cement.

Thus the invention provides a cement slurry comprising:

- 25
- a solid fraction constituted by 35% to 80% (by volume) of particles with a mean diameter in the range 100 microns (μ) to 800 μ ; 0% to 15% (by volume) of particles with a mean particle diameter in the range 0.1 microns to 10 microns; and 10% to 40% (by volume) of particles with a mean particle diameter in the range 20 μ to 50 μ ; a fraction of said solid particles being constituted by a cement;
- 30
- a liquid fraction in a water/solid ratio in the range 38% to 50% by volume; and
 - a percentage of cells, provided by a gas or a liquid which is not miscible with water, in the range 30% to 60% of the final volume of the slurry.

WO 01/87796

PCT/EP01/05507

In a particularly preferred variation of the invention, a fraction of the solid particles is constituted by particles which are destroyed during or after cement settings. The idea is to create cells in a cement slurry containing coarse particles. To this end, it can either be pre-foamed or the slurry or the paste can be emulsified with a fluid which is not miscible with water. Once the cement has set, these cells are then interconnected in part only. Almost complete interconnection is achieved by destruction of coarse particles connecting the cells. Suitable coarse particles include cenosphere type particles wherein destruction is brought on by the chemical environment in the setting of the cement and by temperature. Under these conditions, after the cement has set, it is possible to obtain a compressive strength of more than 3.4 MPa (500 pounds per square inch, psi) and a water permeability of more than 1 Darcy.

The invention has many applications both in the petroleum industry and in the civil engineering or construction industry. Some non-limiting examples which can be cited are:

In the oil well repair field:

- Replacing portions of the reservoir behind the casing which have disintegrated over time and by fluid circulation. This often occurs when the well produces water from the reservoir or from another geological layer which is poorly isolated from the reservoir (cross-flow). The operation, which consists of filling the void left behind the casing by the disintegrated rock with a porous high-strength material that can resist the pressure drop generated by fluid flow, is absolutely vital for carrying out matrix treatment.
- Stopping the production of sand from a well. When the reservoir is constituted by sand, which may or may not be consolidated, or by poorly bound sandstone or where the binder can be dissolved by water, erosion due to fluid flow entrains grains of sand. That production of sand can lead to a stoppage in well production. To avoid such a situation, a gravel packing or filter screens are normally installed inside the well to stop the sand. Over time, these can become soiled or blocked with fine particles. Replacing them is difficult and expensive. Using a permeable cement behind the casing can prevent it being necessary to perform this operation.
- Simple replacement of the cement behind the casing. This can be carried out with a conventional cement, but then the casing and the new layer of cement needs to be perforated again to re-connect the well to the reservoir, with the risk of the

WO 01/87796

PCT/EP01/05507

connection not being made if the cement layer is thicker than planned or perforation is not deep enough. Injecting permeable cement costs less and guarantees that connection will be established in all cases.

5 In the field of new well construction

- When the strength of the formation is sufficient to allow it, the costs related to placing a casing are avoided by carrying out what is known as an uncased or barefoot completion. Sand packing or gravel packing is then installed if the reservoir might produce sand. A pre-perforated blank liner can also be employed.
10 Placing a layer of permeable cement at the surface of the well walls can avoid the need for such operations. Furthermore, when the formation of the reservoir is not sufficiently strong for that type of simplified completion and it would otherwise have been necessary to put a casing into position with cementing between the casing and the well wall, putting the permeable cement of the invention into
15 position can reinforce the sides of the well and can avoid the need for a casing and subsequent perforation thereof.
- When completion with a casing is unavoidable because the rock of the reservoir is very poorly consolidated, placing the permeable cement of the invention between the casing and the sides of the well, instead of a conventional cement, can avoid
20 the need for installing gravel packing or sand packing which is very expensive.

In all cases, the novel material of the invention is particularly suitable for non-consolidated or poorly consolidated sand or fissured or faulted rock. Advantageously, it can also be used for reservoir rock rendered fragile by exhaustion of the field. Clearly, these applications are valid
25 for crude oil or gas producing wells, for subterranean gas storage wells, for wells producing water or other fluids, and regardless of whether the cemented portion is vertical, horizontal, or merely inclined. The application to practically horizontal wells is of particular interest.

The formulation contains at least two types of particle (including cement), and preferably 3 or
30 4 types, with self-destructive particles. The cement can be of any nature, Portland cement which may or may not include pozzolanic material such as blast furnace slag or fly ash or natural materials such as pozzolana or calcined clays. It is also possible to use high-alumina

WO 01/87796

PCT/EP01/05507

cements also known as Ciment Fondu, plaster, Sorel cement, activated pozzolanic cements or any other hydraulic cement.

5 The slurry or cement paste includes particles which are destroyed after setting to create the interconnections and thus increase the permeability of the final material. Cells are created in the cement slurry or paste before setting, either by forming a foam or by emulsifying a fluid which is not miscible with water in the slurry or paste.

10 If all or some of the coarse particles are constituted by cenospheres, the permeability is very significantly increased without altering the compressive strength of the material (see Example 2). This results from a chemical modification of the core of these hollow particles which occurs when the cement sets and thus its kinetics are temperature-dependent. The porosity constituted by the insides of these hollow particles is then liberated, thus substantially increasing the connections between cells.

15

Among these numerous possibilities, a combination comprising four types of particle, namely a Portland cement, fine particles with a mean size of about 3 microns, hollow cenospheres, and very coarse particles (more than 200 microns) is our generally preferred case. Depending on requirements, different known additives can be added to the slurry or paste, such as
20 dispersing agents, retarding agents or accelerators, or fluid loss control agents. In the case of a Portland cement, when the temperature is over 105°C, silica is added in a proportion of 30% to 50% by weight relative to the cement, as is known in the art to prevent retrogression of compressive strength.

25 The fine particles can be constituted by a micro-cement when the compressive strength of the porous cement has to be high.

EXAMPLE 1

30 The properties of a slurry prepared in accordance with the invention are presented and compared with those of a slurry for a conventional foamed system having the same foam quality, namely 40%:

WO 01/87796

PCT/EP01/05507

Slurry A: A mixture of powders was prepared. It comprised 30% by volume of haematite particles with a mean size of about 300 microns; 30% by volume of silica with a mean size of 300 microns; 30% by volume of class G Portland cement and 10% by volume of a Portland/slag micro-cement with a mean size of about 3 microns.

5

Water and a polynaphthalene sulfonate-based super-plasticizer in an amount of 0.07 gallons per sack of powder was mixed with this powder such that the volume percentage of liquid in the slurry was 40%. It should be noted that a sack of powder is defined by analogy with a sack of cement, one sack being 45.359 kg of mixture. In other words, 1 gps = 0.0834 litres (l) of additive per kg of mixture.

10

Slurry B (reference): This slurry corresponded to the prior art. It comprised a class G cement and water such that the density of the slurry was 1900 kg/m³ (15.8 pounds per gallon, ppg).

15 These two slurries were foamed using the same procedure, after adding surfactants (D139 – a mixture of polyglycols, oxyalkylates and methanol; and F052.1 – ethoxysulphonate surfactants in solvents) in an amount of 0.084 gallons per sack of powder (0.007 l/kg), to obtain a foam quality of 40% (i.e., the volume of the foam represented 40% of the final volume of the foamed slurry).

20

Slurry	A (invention)	B (reference)
Porosity before foaming	40%	59%
Foam quality	40%	40%
Compressive strength, MPa (psi)	5.17 (750)	5.93 (860)
Water permeability (Darcy)	0.150	0.008

The compressive strength and water permeability were measured using samples which were left at ambient temperature and at atmospheric pressure for 48 hours (h) then oven dried at 85°C for 5 days. The compressive strength is expressed in MPa, with pounds per square inch (psi) in brackets.

25

WO 01/87796

PCT/EP01/05507

EXAMPLE 2

5 The properties of two slurries prepared in accordance with the invention, one without destructive particles, the other with destructive particles, are presented and compared:

10 Slurry A: A mixture of powders was prepared. It comprised 30% by volume of haematite particles with a mean size of about 300 microns; 30% by volume of silica with a mean size of 300 microns; 30% by volume of class G Portland cement and 10% by volume of a Portland/slag micro-cement with a mean size of about 3 microns.

15 Water and a polynaphthalene sulfonate-based super-plasticizer in an amount of 0.07 gallons per sack of powder (0.006 l/kg) was mixed with this powder such that the volume percentage of liquid in the slurry was 40%.

20 Slurry C: A mixture of powders was prepared. It comprised 30% by volume of haematite particles with a mean size of about 300 microns; 30% by volume of hollow cenospheres with a mean size of 180 microns; 30% by volume of class G Portland cement and 10% by volume of a Portland/slag micro-cement with a mean size of about 3 microns.

Water and a polynaphthalene sulfonate-based super-plasticizer in an amount of 0.07 gallons per sack of powder (0.006 l/kg) was mixed with this powder such that the volume percentage of liquid in the slurry was 40%.

25 These two slurries were foamed using the same procedure, after adding surfactants (D139 and F052.1) in an amount of 0.084 gallons per sack of powder (0.007 l/kg), to obtain a foam quality of 40% (i.e., the volume of the foam represented 40% of the final volume of the foamed slurry).

WO 01/87796

PCT/EP01/05507

Slurry	A (invention)	C
Porosity before foaming	40%	40%
Compressive strength, MPa (psi)	5.17 (750)	5.59 (810)
Water permeability (Darcy)	0.150	1.2

The compressive strength and water permeability were measured using samples which were left at ambient temperature and at atmospheric pressure for 48 h then oven dried at 85°C for 5 days.

5

EXAMPLE 3

The properties of five slurries prepared in accordance with the invention but foamed with different foam qualities are presented and compared:

10

Basic slurry: A mixture of powders was prepared. It comprised 30% by volume of haematite particles with a mean size of about 300 microns; 30% by volume of hollow spheres with a mean size of 180 microns; 30% by volume of class G Portland cement and 10% by volume of a Portland/slag micro-cement with a mean size of about 3 microns.

15

Water and a polynaphthalene sulfonate-based super-plasticizer in an amount of 0.07 gallons per sack of powder (0.006 l/kg) was mixed with this powder such that the volume percentage of liquid in the slurry was 40%.

20

Surfactants were added to the basic slurry and the slurries were foamed to obtain a foam quality of 30% to 50%. It should be remembered that a foam quality of 30% means that the foam volume represents 30% of the final volume of the slurry.

WO 01/87796

PCT/EP01/05507

Slurry	C1	C2	C3	C4	C5
Porosity before foaming	40%	40%	40%	40%	40%
Foam quality	30%	35%	40%	45%	50%
Compressive strength, MPa (psi)	8.27 (1200)	6.90 (1000)	5.59 (810)	4.48 (650)	2.83 (410)
Water permeability (Darcy)	0.0045	0.160	1.2	6.1	>12

The compressive strength and water permeability were measured using samples which were left at ambient temperature and at atmospheric pressure for 48 h then oven dried at 85°C for 5 days.

5

EXAMPLE 4

The properties of two slurries prepared in accordance with the invention, both containing self-destructive particles but with coarse particles of differing size and nature, are presented and compared:

10

Slurry C: A mixture of powders was prepared. It comprised 30% by volume of haematite particles with a mean size of about 300 microns; 30% by volume of hollow cenospheres with a mean size of 180 microns; 30% by volume of class G Portland cement and 10% by volume of a Portland/slag micro-cement with a mean size of about 3 microns.

15

Water and a polynaphthalene sulfonate-based super-plasticizer in an amount of 0.07 gallons per sack of powder (0.006 l/kg) was mixed with this powder such that the volume percentage of liquid in the slurry was 40%.

20

Slurry D: A mixture of powders was prepared. It comprised 30% by volume of calcium carbonate particles with a mean size of about 500 microns; 30% by volume of hollow cenospheres with a mean size of 180 microns; 30% by volume of class G Portland cement and 10% by volume of a Portland/slag micro-cement with a mean size of about 3 microns.

25

WO 01/87796

PCT/EP01/05507

Water and a polynaphthalene sulfonate-based super-plasticizer in an amount of 0.07 gallons per sack of powder (0.006 l/kg) was mixed with this powder such that the volume percentage of liquid in the slurry was 40%.

- 5 These two slurries were foamed using the same procedure, after adding surfactants (D139 and F052.1) in an amount of 0.084 gallons per sack of powder (0.007 l/kg), to obtain a foam quality of 35% (i.e., the volume of the foam represented 35% of the final volume of the foamed slurry).

Slurry	C	D
Porosity before foaming	40%	40%
Compressive strength	6.90 (1000)	5.79 (840)
Water permeability (D)	0.160	0.270

10

The compressive strength and water permeability were measured using samples which were left at ambient temperature and at atmospheric pressure for 48 h then oven dried at 85°C for 5 days.

WO 01/87796

PCT/EP01/05507

CLAIMS

- 1 A cement slurry comprising:
a solid fraction constituted by:

5 35% to 80% (by volume) of particles with a mean size in the range
100 microns (μ) to 800 μ ;

0% to 15% (by volume) of particles with a mean particle diameter in the range
0.1 microns to 10 microns; and

10 10% to 40% (by volume) of particles with a mean particle diameter in the
range 20 μ to 50 μ ;

a fraction of said solid particles being constituted by a cement;

a liquid fraction in a water/solid ratio in the range 38% to 50% by volume; and

a percentage of cells, provided by a gas or a liquid which is not miscible with water, in
the range 30% to 60% of the final volume of the slurry.

- 15 2 A cement slurry according to the preceding claim, characterized in that it comprises
haematite particles.

- 3 A cement slurry according to either preceding claim, characterized in that a portion of
the solid particles is constituted by particles having a structure that is destroyed during
20 the setting of the cement.

- 4 A cement slurry according to claim 3, characterized in that said portion of the solid
particles comprises hollow spheres originating from cenospheres.

- 25 5 A cement slurry according to claim 4, characterized in that it further comprises
calcium carbonate particles.

- 6 A cement slurry according to any preceding claim, characterized in that the mean
diameter of said particles is in the range 0.1 to 10 microns and is constituted by a
30 micro-cement or a micro-cement/slag mixture.

WO 01/87796

PCT/EP01/05507

7 A cement obtained after setting a slurry according to any one of the preceding claims, having a compressive strength of more than 3.4 MPa and a water permeability of more than 1 Darcy.

5 8 A method of remedial treatment of voids behind casing in a borehole, comprising pumping a cement slurry into the void and allowing it to set, the cement slurry comprising:

a solid fraction constituted by:

10 35% to 80% (by volume) of particles with a mean size in the range 100 microns (μ) to 800 μ ;

0% to 15% (by volume) of particles with a mean particle diameter in the range 0.1 microns to 10 microns; and

10% to 40% (by volume) of particles with a mean particle diameter in the range 20 μ to 50 μ ;

15 a fraction of said solid particles being constituted by a cement;

a liquid fraction in a water/solid ratio in the range 38% to 50% by volume; and

a percentage of cells, provided by a gas or a liquid which is not miscible with water, in the range 30% to 60% of the final volume of the slurry.

20 9 A method of completing a well, comprising pumping a cement slurry into an annulus around a casing, screen or slotted liner placed in a well and allowing it to set, the cement slurry comprising:

a solid fraction constituted by:

25 35% to 80% (by volume) of particles with a mean size in the range 100 microns (μ) to 800 μ ;

0% to 15% (by volume) of particles with a mean particle diameter in the range 0.1 microns to 10 microns; and

10% to 40% (by volume) of particles with a mean particle diameter in the range 20 μ to 50 μ ;

30 a fraction of said solid particles being constituted by a cement;

a liquid fraction in a water/solid ratio in the range 38% to 50% by volume; and

a percentage of cells, provided by a gas or a liquid which is not miscible with water, in the range 30% to 60% of the final volume of the slurry.

WO 01/87796

PCT/EP01/05507

10 A method of preventing sand production from an underground formation into a well, comprising pumping a cement slurry into a region adjacent the formation and allowing it to set, the cement slurry comprising:

5 a solid fraction constituted by:

35% to 80% (by volume) of particles with a mean size in the range 100 microns (μ) to 800 μ ;

0% to 15% (by volume) of particles with a mean particle diameter in the range 0.1 microns to 10 microns; and

10 10% to 40% (by volume) of particles with a mean particle diameter in the range 20 μ to 50 μ ;

a fraction of said solid particles being constituted by a cement;

a liquid fraction in a water/solid ratio in the range 38% to 50% by volume; and

15 a percentage of cells, provided by a gas or a liquid which is not miscible with water, in the range 30% to 60% of the final volume of the slurry.

11 A method of replacing eroded cement behind a casing in a well, comprising pumping a cement slurry into the region of the eroded cement and allowing it to set, the cement slurry comprising:

20 a solid fraction constituted by:

35% to 80% (by volume) of particles with a mean size in the range 100 microns (μ) to 800 μ ;

0% to 15% (by volume) of particles with a mean particle diameter in the range 0.1 microns to 10 microns; and

25 10% to 40% (by volume) of particles with a mean particle diameter in the range 20 μ to 50 μ ;

a fraction of said solid particles being constituted by a cement;

a liquid fraction in a water/solid ratio in the range 38% to 50% by volume; and

30 a percentage of cells, provided by a gas or a liquid which is not miscible with water, in the range 30% to 60% of the final volume of the slurry.

12 A method of selectively producing oil from an oil and water producing formation, comprising pumping a cement slurry into or adjacent to a producing formation.

WO 01/87796

PCT/EP01/05507

allowing the cement to set, so as to produce fluid from the reservoir with an oil water ratio higher than would normally be possible from an untreated formation, the cement slurry comprising:

a solid fraction constituted by:

5 35% to 80% (by volume) of particles with a mean size in the range 100 microns (μ) to 800 μ ;

0% to 15% (by volume) of particles with a mean particle diameter in the range 0.1 microns to 10 microns; and

10 10% to 40% (by volume) of particles with a mean particle diameter in the range 20 μ to 50 μ ;

a fraction of said solid particles being constituted by a cement;

a liquid fraction in a water/solid ratio in the range 38% to 50% by volume; and

a percentage of cells, provided by a gas or a liquid which is not miscible with water, in the range 30% to 60% of the final volume of the slurry.

INTERNATIONAL SEARCH REPORT

Intern Application No

PC1/EP 01/05507

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C04B28/02 C04B38/10 E21B43/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C04B E21B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	WO 00 29351 A (SOFITECH NV ; SCHLUMBERGER CA LTD (CA); SCHLUMBERGER CIE DOWELL (FR) 25 May 2000 (2000-05-25) claims	1,6,9
P,A	WO 01 09056 A (SOFITECH NV ; SCHLUMBERGER CA LTD (CA); DROCHON BRUNO (FR); GARNIER) 8 February 2001 (2001-02-08) claims	1,9
A	FR 2 749 843 A (SCHLUMBERGER CIE DOWELL) 19 December 1997 (1997-12-19) claims	1-5,9
A	EP 0 814 067 A (SOFITECH NV) 29 December 1997 (1997-12-29) page 3, line 25 - line 39	1,3,4,9
-/-		

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- *A* document member of the same patent family

Date of the actual completion of the international search

28 August 2001

Date of mailing of the international search report

04/09/2001

Name and mailing address of the ISA

European Patent Office, P.O. 5818 Patentkan 2
NL - 2280 HV Rijswijk
Tel (+31-70) 940-2040, Tx. 31 651 epo nl
Fax (+31-70) 940-3016

Authorized officer

Theodoridou, E

INTERNATIONAL SEARCH REPORT

Interr Application No
PC1/Er 01/05507

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 3 707 914 A (LAND K) 2 January 1973 (1973-01-02) column 4, line 56 -column 5, line 9	1,3,4,9

Form PCT/SA/210 (continuation of second sheet) (July 1992)

page 2 of 2

RECEIVED TIME MAY. 21. 8:54AM

INTERNATIONAL SEARCH REPORT

information on patent family members

Intern. Application No
PCT/EP 01/05507

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0029351	A	25-05-2000	WO 0029351 A1	25-05-2000
			AU 1241999 A	05-06-2000
			NO 20012352 A	05-07-2001
WO 0109056	A	08-02-2001	FR 2796935 A1	02-02-2001
			AU 6270200 A	19-02-2001
			WO 0109056 A1	08-02-2001
FR 2749843	A	19-12-1997	FR 2749843 A1	19-12-1997
			FR 2749844 A1	19-12-1997
			US 6060535 A	09-05-2000
EP 0814067	A	29-12-1997	FR 2749844 A1	19-12-1997
			CA 2207885 A1	18-12-1997
			EP 0814067 A1	29-12-1997
			NO 972799 A	19-12-1997
			US 6060535 A	09-05-2000
US 3707914	A	02-01-1973	CA 941734 A1	12-02-1974

RECEIVED TIME MAY. 21. 8:54AM